

POLYPRO ULTRA

Polypropylene with special additives to improve its adhesion to the printing surface. Very versatile material, transparent, light and flexible. It also has excellent mechanical and chemical resistance making it ideal for industrial applications.

Physical Properties	Typical Value	Test Method
<i>Material Density</i>	0,9 g/cm ³	ISO 1183
<i>Chemical Name</i>	Polypropylene	
Thermal Properties	Typical Value	Test Method
<i>Heat Distorsion Temperature</i>	62 °C	ISO 75
<i>Vicat Softening Temperature</i>	107 °C	ISO 306
Printing Properties	Typical Value	
<i>Print Temperature</i>	220±10 °C	
<i>Hot Pad</i>	60-100 °C	
<i>Fan Layer</i>	On (100%)	



Recyclable
Recyclable



Food Approved
Aliments approuvés